



Atik Vinyl Sheet 70

Technical Specification

Flooring Type	EN 13845	Safety Flooring
Heterogeneous PVC	ISO 10582 EN 13845	Not recommended for very wet areas as swimming pools and showers
Level of use	EN ISO 10874	34-43
Total thickness	EN ISO 24346	2,00 mm
Wear layer	EN ISO 24340	0,7 mm
Wear layer PUR treatment		HyperGrip
Total weight/m ²	EN ISO 23997	ca. 2.850 g
Width	EN ISO 24341	2 m
Standard Length	EN ISO 24341	ca. 20 m
Weight of standard roll		ca. 118 kg
Inflammability	EN 13501	Bfl-S1*
Slip resistance	EN 13893	DS
Slip restraint	EN 16165	R12
Slip classification	EN 13845	Class ESf - ESb
Abrasion resistance test	EN 13845	< 10% particles lost over 50.000 Cycles
Pendulum test (Wet Test)	EN 16165	36+ Low slip risk potential
Fonghi-bacterio static treatment		Sanitec
Residual indentation	EN ISO 24343-1	0,04 mm (norm ≤ 0,10 mm)
Furniture leg resistance	EN ISO 16581	Very good
Curling	EN ISO 23999	≤ 8 mm
Electrical resistance	EN 1081	6,4 x 10 ⁸ Ohm
Static electrical propensity	EN 1815	≤ 2kV (antistatic)
Dimensional stability	EN ISO 23999	≤ 0,10% (norm ≤ 0,40%)
Thermal conductivity	EN ISO 10456	0,164 W/(m.K)
Heat insulation	EN 12667	0,0134 (m ² .K/W)

The warranty covers manufacturing defects and premature wear in the event of normal use





Atik Vinyl Sheet 70

Technical Specification

Binder quantity in wear layer	EN ISO 10582	Type I
Abrasion group	EN 660-2	Class T
Indoor air quality		LOW VOC
Acoustic insulation	EN ISO 717-2	ΔL_w 5 dB
Castor chair resistance	EN ISO 4918	Pass
Castor type	EN 12529	Type W
Light fastness	ISO 105B02	6
Underfloor heating	EN 12524	Suitable
Resistance to chemicals	EN ISO 26987	Very good
Hot welding		Available
Cold welding	Invisiweld	Suitable
Warranty years		10

The warranty covers manufacturing defects and premature wear in the event of normal use

